

SECTION 03 30 00**CONCRETE**

(Sentences and/or paragraphs that are double underlined indicate revisions that were made from the 2008 specification.)

PART 1 - GENERAL**1.1 DESCRIPTION**

- A. This specification shall govern for Portland cement concrete to be used in concrete pavement, concrete structures and other concrete construction.

1.2 MEASUREMENT AND PAYMENT

- A. In general and unless otherwise specified, no separate payment will be made for concrete as an item. The cost of concrete including all materials and equipment, furnishing and placing all reinforcing steel, and performing all labor for the manufacturing, transporting, placing, finishing, and curing of concrete will be included in the unit price bid for specific items as set forth in the Proposal. Payment will not be made for unauthorized work.

1.3 SUBMITTALS

List of Admixtures proposed
 Concrete Mix Designs and three sets of tests on the mix designs submitted.
 Certification for cement conformance to specification
 Test reports for all required concrete tests
 Mill report/Certifications for all Reinforcing Bar.
 Material Data on Control, Expansion and Contraction Joint materials and sealants.

PART 2 – PRODUCTS**2.1 MATERIALS****A. PORTLAND CEMENT:**

Cement shall be Type I, II or III Portland Cement conforming to ASTM C150, or Type IA, IIA or IIIA, conforming to ASTM C175 except as noted below.

1. Different types of cement, as prescribed above may be used in the same structure, but all cement used in any one monolithic placement shall be of the same type and brand.
2. Type III cement shall not be used when the anticipated air temperature for the succeeding 12 hours will exceed 60° F.

B. FLY ASH:

Fly Ash shall be Type C or F Fly Ash in accordance with ASTM C618. When fly ash is used, “cement” shall be defined as “cement plus fly ash”. “Cement plus fly ash” shall be composed of Type I, II or III Portland cement and 20 to 35 percent fly ash by absolute volume, except that for classes of concrete which are specified to have less than five (5) sacks of Portland cement per cubic yard, the fly ash replacement of cement shall not exceed 25 percent by absolute volume of

the specified cement content.

C. AGGREGATE:

1. Concrete aggregate shall conform to all requirements of Texas Department of Transportation Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges (2004) Section 421.2 E 1, 2 and 3, and ASTM C33.
2. The maximum size of aggregate shall not be larger than one-fifth of the narrowest dimension between forms of the member for which concrete is to be used nor larger than three-fourths of the minimum clear spacing between reinforcing bars.

D. WATER:

Water for use in concrete and for curing shall be from municipal supplies approved by the Texas Commission on Environmental Quality and Texas Department of Health or shall conform to the provisions of AASHTO T26 for quality of water.

E. REINFORCING STEEL:

1. The reinforcing steel shall be Grade 60.
2. Steel reinforcing bars as required, shall be of the type and size as shown on Plans and shall be open hearth new billet steel of structural, intermediate, or hard grade, or shall be rail steel concrete reinforcement bars. All steel shall be bent cold.
3. New billet steel shall conform to the requirements of the Standard Specifications for Billet-Steel Concrete Reinforcement Bars, ASTM Designation A-15.
4. When fabricated steel bar or rod mats are specified, the mats shall meet the current requirements of specifications for Fabricated Steel Bar or Rod Mats for Concrete Reinforcement ASTM Designation A-184.
5. In the event reinforcing bars manufactured outside of the Continental United States or its territories are used, two sets of tests from an independent testing laboratory acceptable to the Engineer shall be submitted showing that the steel meets the ASTM Standards for tensile strength, phosphorus content, bend, deformations and such other requirements outlined in the ASTM Standards for the grade used. These tests shall be made by and independent testing laboratory at the Contractor's expense and shall be submitted for each 25 tons of steel supplied from each individual mill.
6. At the time of placement in the concrete, reinforcing steel shall be free of dirt, loose rust, mill scale, paint, grease, oil or other deleterious materials that would impair the bonding of the concrete to the steel.
7. Reinforcement shall be accurately positioned and, unless otherwise shown or specified, shall be secured against displacement by using at intersection, annealed iron wire of not less than No. 18 gauge or suitable metal clips. It shall be supported by plastic or metal chairs or spacers. In general, reinforcement shall be placed, spliced, lapped, located, etc., in accordance with the recommendations of the Concrete Reinforcement Steel Institute or Texas Department of Transportation Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges (2004) Section 440.
8. Under no circumstances shall reinforcing steel or dowel bars be “stabbed” into fresh concrete. When reinforcing steel or dowel bars are required to extend beyond the slip-

formed surface, holes shall be drilled and the steel shall be epoxyed into place using a pre-approved epoxy.

F. STORAGE OF MATERIALS:

1. All cement, fly ash and mineral filler shall be stored in well-ventilated weatherproof buildings or pre-approved bins, which will protect them from dampness or absorption of moisture.
2. The method of handling and storing concrete aggregates shall prevent contamination with foreign materials. To assure uniform concrete, aggregate stockpiles shall be maintained at reasonably uniform moisture content.

2.2 TESTING REQUIREMENTS

A. CONCRETE QUALITY AND ALLOWABLE STRESSES

1. Concrete Quality:

Concrete mixes will be designed and made in sufficient number to represent the required water-cement ratios. These mixes shall comply with the requirements prescribed for strength and consistency as shown below. The Contractor shall furnish the results on trial mixes from a testing laboratory pre-approved by the Engineer.

Minimum Compressive Strength, psi at 28 days	Minimum Cement Content Sack/cubic yard	Maximum Water Content Gal/sack of cement	General Usage
1,500	3.0	11.0	Riprap
3,000	4.5	6.0	Drilled Shaft, Inlets; Manholes; Headwalls; Sidewalks; Driveways;
3,500	5.0	6.0	Concrete Pavement; curb and gutters
4,000	5.5	5.0	Bridge slab; Culverts

The slump of concrete mixtures shall be within the following limits when measured according to "Test for Slump of Portland Cement Concrete" (ASTM C142). When admixtures are used to increase the workability, the mix design shall indicate the slump before and after its introduction into the mix.

TYPE OF CONSTRUCTION	COMPRESSIVE STRENGTH OF CONCRETE, psi	MAXIMUM SLUMP (before admixtures)
Concrete Pavement	3,500	3"
Curb and Gutter	3,500	3"
Sidewalk	3,000	5"
Drilled Shafts and Footings	3,000	7"

Thin Walled Sections (9” or less)	3,000	5”
Thick Walls	By Special Design	

B. TESTS ON CONCRETE

1. During the progress of the work, compression test specimens shall be made and cured in accordance with "Standard Method of Making and Curing Concrete Compression and Flexure Test Specimens in the Field" (ASTM C31). Not less than three specimens shall be made for each test, nor less than one test for each 50 cubic yards or fraction thereof of concrete placed or for each day’s pour. These tests shall be made by an independent testing laboratory at the Owner's expense.
2. Specimens shall be tested in accordance with "Standard Method of Test for Compressive Strength of Molded Concrete Cylinders" (ASTM C39).
3. The standard age of test shall be 7 days and 28 days.
4. If the average strength of the control cylinders for any portion of the structure falls below the specified compressive strength, the Engineer shall have the right to order changes in the proportions or the cement content for the remaining portion of the structure. If the concrete minimum 28 day strength is not achieved the Engineer shall have the right to order its removal.
5. An air-entraining admixture may be used with Type I, II, or III Portland Cement in lieu of an Air-Entraining Portland Cement. The admixture shall meet the requirements of "Specifications for Air-Entraining Admixtures for Concrete" (ASTM C260). Concrete produced from either Type IA, IIA, or IIIA cement or the use of air-entraining admixtures shall have an air content from 3 to 5 percent when determined by means of the test for air-content, ASTM C231.

C. TEST CYLINDERS

Preparation of test cylinders and tests on concrete cylinders shall be made at the expense of the Owner. The cost of all failed tests shall be charged to the Contractor.

PART 3 – EXECUTION

3.1 CONSTRUCTION METHODS

A. PREPARATION OF EQUIPMENT AND PLACE OF DEPOSIT:

1. Before placing concrete, all equipment for mixing and transporting the concrete shall be cleaned. All debris shall be removed from the place to be occupied by the concrete.
2. Water shall be removed from place of deposit before concrete is placed unless otherwise permitted by the Engineer.

B. MIXING OF CONCRETE

1. The concrete shall be mixed until there is a uniform distribution of materials and shall be discharged completely, before the mixer is recharged.
2. For job-mixed concrete, the mixer shall be rotated at a speed recommended by the

manufacturer. Mixing shall be continued at least one (1) minute after all materials are in the mixer. Job-mixed concrete shall be rejected and disposed of as directed if not placed as prescribed within thirty (30) minutes after beginning of mixing. Job-mixed concrete is only allowed with written approval from the City Engineer 72-hours prior to the pour.

3. Ready-mixed concrete shall be measured, mixed and delivered in accordance with the requirements set forth in "Standard Specifications for Ready-Mixed Concrete" (ASTM C-94).

C. CONVEYING

1. Concrete shall be conveyed from the mixer to the place of final deposit by methods which will prevent the separation or loss of the materials.
2. Equipment for chuting, pumping, and pneumatically conveying concrete shall be of a size and design to insure a continuous flow of the concrete at the delivery point, without separation of the materials.

D. TRANSPORTATION EQUIPMENT

Transportation of concrete mixed completely in a stationary mixer, from the mixer to the point of placement, shall be by truck agitator, or in a truck mixer operating at agitator speed, or in non-agitating equipment conforming to ASTM Standard C-94 except as modified herein. Truck agitators, truck mixers, and non-agitating equipment shall be capable of delivering concrete without segregation in transit. Slump tests of individual samples taken at approximately the one-quarter and three-quarter points of the load during discharge shall not vary by more than 1 inch. Vehicles transporting concrete mixed partially or completely in stationary mixers shall be equipped with discharge chutes or other devices when operating outside of the prepared subgrade, or shall be supplemented by additional transfer equipment capable of discharging or transferring the concrete from the transporting vehicle to its final position in the form without segregation.

E. FACILITIES FOR SAMPLING

Suitable facilities shall be provided for readily obtaining representative samples of aggregate from each of the bins or compartments for test purposes. Suitable facilities shall be provided for obtaining representative samples of concrete for uniformity tests. All necessary platforms, tools, and equipment for obtaining samples shall be furnished by the Contractor.

F. PLACING CONCRETE

1. The Contractor shall give the Engineer a minimum 24 hours advance notice before placing concrete to permit the inspection of forms, reinforcing steel placement and other preparations.
2. Concrete placement will not be permitted when impending weather conditions would impair the quality of the finished work.
3. Transporting Time: The maximum time interval between the addition of cement to the batch and the placing of concrete in the forms shall conform to the requirements below:

Concrete Temp (at point of placement)	Max Time (No Retarding Agent)	Max Time (with Retarding Agent)
--	----------------------------------	------------------------------------

	Minutes)	Minutes
Non-Agitated Concrete		
Above 80 F	15	30
80 F and Below	30	45
Agitated Concrete		
Above 90 F	45	75
Above 75 F thru 90 F	60	90
75 F and Below	90	120

4. All forms, sub grade and steel shall be dampened before placement of concrete to assist with retaining moisture in the concrete.

5. Cold Weather Precautions:

Concrete shall not be placed when the ambient temperature is below 40° F and falling. Concrete may be placed when the ambient temperature is above 35° F and rising, the ambient temperature being taken in the shade and away from artificial heat. Concrete shall not be placed when the forecast predicts 72 continuous hours of temperatures less than 32° F.

The Contractor shall have available a sufficient supply of pre-approved cotton mats, polyethylene sheeting or other pre-approved covering materials to immediately protect concrete if the air temperature falls to 32° F, or below, before concrete has been in place for less than four (4) hours. Such protection shall remain in place during the period the temperature continues below 32° F, or for a period of not more than five (5) days. Neither salt nor other chemical admixtures shall be added to the concrete to prevent freezing. The Contractor shall be responsible for the quality and strength of concrete under cold weather conditions and any concrete damaged by freezing shall be removed and replaced at the Contractor’s expense.

The surface of all concrete in bents, piers, culvert walls, retaining walls, bottom of slabs, and similar formed concrete shall be maintained at 40° F or above for a period of 72 hours from the time of placements. The temperature of all concrete, including the bottom slabs (footings) of culverts placed on or in the ground, shall be maintained above 32° F for a period of 72 hours from time of placement.

Protection shall consist of providing additional covering, insulated forms or other means, and if necessary, supplementing such coverings with artificial heating.

6. Warm Weather Precautions

The following precautions shall be taken in placing, curing, and protecting the concrete when local weather records show that the maximum daily temperature is likely to exceed 95° F. The forms and the subgrade, subbase or base course shall be sprinkled with water immediately before placing the concrete. The concrete shall be placed at the coolest temperature practicable, and in no case shall the temperature of the concrete exceed 95° F when deposited on the subgrade, subbase or base course. The temperature of the concrete shall not exceed 85° F for bridge slabs or in the top slab of direct-traffic culverts. The aggregates and/or mixing water will be cooled as necessary to maintain the concrete temperature within the specified maximum. Concrete shall be placed in the forms continuously and rapidly at a rate of not less than 100 feet of paving lane per hour. The surface of the newly laid pavement shall be kept damp by means of a water fog or mist applied with pre-approved spraying equipment until the pavement is covered by the pre-

approved curing medium.

7. Concrete shall be deposited as nearly as practicable in its final position to avoid segregation due to rehandling or flowing. The deposition shall be at a rate that allows the concrete to be plastic at all times and permits flow readily into the space between the rebar. Retempered concrete shall not be used and concrete shall not have a free fall of more than five (5) feet, except in the case of thin walls such as in culverts or as specified in other items. Any hardened concrete spatter ahead of the plastic concrete shall be removed.
8. Concrete deposition shall be a continuous operation until completed at the panel or section. Cold joints in a monolithic placement shall be avoided. The sequence of successive layers or adjacent portions of concrete shall be such that they can be vibrated into a homogeneous mass with the previously placed concrete. Not more than one (1) hour shall elapse between adjacent or successive placements of concrete.
9. Concrete shall be thoroughly consolidated and vibrated in the forms with pre-approved mechanical vibrators of a type considered in the design of forms.

G. FINISHING

Unless noted otherwise, apply an ordinary surface finish as the final finish to the following exposed surfaces:

- inside and top of inlets,
- inside and top of manholes,
- inside of sewer appurtenances,
- inside of culvert barrels, bottom of bridge slabs between girders and beams, and
- vertical and bottom surfaces of interior concrete beams or girders.

An ordinary surface finish shall be as follows:

- Chip away all loose or broken material to sound concrete where porous, spalled, or honeycombed areas are visible after form removal.
- Repair spalls by saw-cutting and chipping at least 1/2 in. deep, perpendicular to the surface to eliminate feather edges. Repair shallow cavities using a latex adhesive grout, cement mortar, or epoxy mortar as pre-approved. Repair large areas using concrete as directed or pre-approved.
- Clean and fill holes or spalls caused by the removal of form ties, etc., with latex grout, cement grout, or epoxy grout as pre-approved. Fill only the holes. Do not blend the patch with the surrounding concrete. On surfaces to receive a rub finish in accordance with Item 427, "Surface Finishes for Concrete," chip out exposed parts of metal chairs to a depth of 1/2 in. and repair the surface.
- Remove all fins, runs, drips, or mortar from surfaces that will be exposed. Smooth all form marks and chamfer edges by grinding or dry-rubbing.
- Ensure that all repairs are dense, well bonded, and properly cured. Finish exposed large repairs to blend with the surrounding concrete where a higher class of finish is not specified.

Finish of Bridge Slabs and related features shall be in compliance with TxDOT Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges (2004) Section 420.4.

F. CURING

The concrete shall be kept wet by spraying with water after attaining its final set and before removing the forms. Bottom forms supporting floor or roof slabs shall remain in place for not less than seven (7) days. The concrete shall have attained a compressive strength of not less than 2,000 psi prior to removal of bottom forms. All other forms may be removed twenty-four hours after completion of concrete placement, providing the weather has allowed the concrete to attain its final set in less than five (5) hours. The forms shall be left on for forty-eight (48) hours whenever the temperature of the air in the shade during pouring is 90° F or over. Curing shall be continued for five days after placement of concrete. This may be done with wet mats, with two applications of Type I (White in color) Liquid-Membrane-Forming Compound meeting requirements of ASTM C309, or with waterproof curing paper meeting the requirements of ASTM C171.

G. CONSTRUCTION JOINTS

Construction joints will be made only at locations shown on the Plans unless written permission is granted by the Engineer to make additional joints. Unless otherwise required, make construction joints square and normal to the forms. Use bulkheads in the forms for all vertical joints. Thoroughly roughen the top surface of a concrete placement terminating at a horizontal construction joint as soon as practical after initial set is attained. Thoroughly clean the hardened concrete surface of all loose material, laitance, dirt, and foreign matter. The surface is to be dampened just prior to casting of concrete against the joint.

END OF SECTION