

SECTION 33 05 01

POLYVINYLCHLORIDE PIPE AND FITTINGS

(Sentences and/or paragraphs that are double underlined indicate revisions that were made from the 2008 specification.)

PART 1 - GENERAL**1.1 DESCRIPTION**

- A. The work specified under this section includes the manufacture, construction and installation of Polyvinylchloride (PVC) pipe and fittings for Water Lines and for Gravity and Pressure Sanitary Sewers.

1.2 REFERENCES

The publications listed below form a part of this Specification to the extent referenced. The publications are referred to in the text by basic designation only.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D1784	Standard Specification for Rigid Poly (Vinyl Chloride) (PVC) Compounds and Chlorinated Poly (Vinyl Chloride) (CPVC) Compounds (Latest Edition)
ASTM F477	Standard Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe (Latest Edition)
ASTM F 1483	Standard Specification for Oriented Poly (Vinyl Chloride), (PVCO) Pressure Pipe (Latest Edition)
ASTM C33	Standard Specification for Concrete Aggregates
ASTM C150	Standard Specification for Portland Cement
ASTM D1598	Standard Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
ASTM D1599	Standard Test Method for Resistance to Short-Time Hydraulic Failure Pressure of Plastic Pipe, Tubing, and Fittings
ASTM D2122	Standard Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
ASTM D2152	Standard Test Method for Adequacy of Fusion of Extruded Poly (Vinyl Chloride) (PVC) Pipe and Molded Fittings by Acetone Immersion
ASTM D2241	Standard Specification for Poly (Vinyl Chloride) (PVC) Pressure-Rated Pipe (SDR Series)
ASTM D2564	Standard Specification for Solvent Cements for Poly (Vinyl Chloride) (PVC) Plastic Piping Systems
ASTM F679	Standard Specification for Poly (Vinyl Chloride) (PVC) Large-Diameter Plastic Gravity Sewer Pipe and Fittings
ASTM D2672	Standard Specification for Joints for IPS PVC Pipe Using Solvent Cement

ASTM D3034	Standard Specification for Type PSM Poly (Vinyl Chloride) (PVC) Sewer Pipe and Fittings
ASTM D3212	Standard Specification for Joints for Drain and Sewer Plastic Pipes Using Flexible Elastomeric Seals
ASTM D3139	Standard Specification for Joints for Plastic Pressure Pipes Using Flexible Elastomeric Seals

AMERICAN WATER WORKS ASSOCIATION (AWWA)

AWWA C900	Polyvinyl Chloride (PVC) Pressure Pipe, 4-Inch Through 12- Inch for Water Distribution (Latest Edition)
AWWA C909	Molecularly Oriented Polyvinyl Chloride (PVCO) Pressure Pipe. 4-Inch Through 12-Inch for Water Distribution (Latest Edition)
AWWA C104	ANSI Standard for Cement-Mortar Lining for Ductile Iron Pipe and Fittings for Water
AWWA C105	ANSI Standard for Polyethylene Encasement for Ductile-Iron Pipe Systems
AWWA C111	ANSI Standard for Rubber-Gasket Joints for Ductile-Iron Pressure Pipe and Fittings
AWWA C116	Protective Fusion Bonded Epoxy Coatings for the Interior and Exterior Surfaces of Ductile-Iron and Gray-Iron Fittings for Water Supply Service
AWWA C153	Ductile Iron Compact Fittings, 3 in. through 24 in. and 54 in. through 64 in. for Water Service
AWWA C905	Polyvinyl Chloride (PVC) Pressure Pipe and Fabricated Fittings, 14 In.-48 In.

1.3 MEASUREMENT AND PAYMENT

- A. Payment shall be made at the price bid per unit length per the specification SECTION 33 11 13.1 - WATER MAIN CONSTRUCTION or SECTION 33 31 13 - SANITARY SEWAGE SYSTEM.

1.4 SUBMITTALS

- A. Submit manufacturer's data on pipe furnished, indicating compliance with the specifications regarding dimensions, thickness, weights, and materials.
- B. Submit manufacturer's "Certificate of Compliance," stating that the materials furnished comply with this specification.

1.5 STORAGE AND HANDLING

A. UNLOADING - COLD WEATHER HANDLING

As the temperature approaches and drops below freezing extra care should be used in handling during cold weather. Pipe at the bottom of a stack may become out-of-round due to the weight of material above it. Allow the pipe to recover to full initial roundness before installation. Pipe may be unloaded by hand, either by passing over the side or off

the truck end. Sliding one length on another is permissible in unloading pipe, but lengths in the bottom layer shall be lifted off of the rough surface of the truck body to avoid abrasion. Compact shipping units (palletized bundles in a wood frame) may be unloaded by conventional fork lifts.

B. STOCKPILES

Store pipe on a flat surface so as to support the barrel evenly with bell ends overhanging. Store random lengths separately where they will be readily available. Individual lengths of pipe should be stacked in piles no higher than 5 feet. Pipe shall be protected during long exposures (over 3 months) to sunlight. Do not use clear plastic sheets. Provide for air circulation under sheet.

C. STORING RUBBER RINGS

Store all rubber rings at a central point and distribute them as needed. Keep them clean, away from oil, grease, excessive heat and electric motors which produce ozone. If rubber rings are not to be used immediately, store them in their cartons, as shipped, in a cool dark place out of the direct rays of the sun.

PART 2 – PRODUCTS

2.1 MATERIALS

A. WATER LINES

1. Pipe

- a. Blue colored Polyvinyl chloride (PVC) pressure pipe, six inch (6”) through twelve inch (12”) , shall conform to the current AWWA – C900 or C909 standard, be UL listed, be approved by the Texas State Board of Insurance and the National Sanitation Foundation. PVC pipe wall thickness shall be based on a working pressure rating of 125 psi at 100° F (DR-14, Class 200 for C900 or Class 200 for C909.). The outside diameter shall be identical to ductile-iron pipe (CIOD Standard, Table 2, AWWA – C900). All pipe shall be new and have the AWWA designation, pressure class, DR pressure rating and size of pipe stamped on the outside of each joint (follow requirements of C900 2.5.2 Markings). All piping shall be new. Partial pieces from other projects shall not be approved for installation. Metal detector tape shall be installed above all PVC pipe at an elevation of 2 feet below natural ground.
- b. Blue colored PVC 4” pipe shall be SDR 21, ASTM D2241.
- c. PVC Pressure Pipe shall be designed and tested in accordance with ASTM D1598, D1599, and D2152.
- d. Fittings for PVC water pipe shall be ductile-iron, and shall conform to AWWA C153, unless otherwise specified.

Fitting joints shall be mechanical joints. Bolts and nuts for mechanical joints, or flanged ends will be of a high strength corrosion resistant low-alloy steel and shall conform to AWWA C111. Flange bolts and nuts for above ground installation shall conform to Appendix A of AWWA C115. Flange bolts and nuts for below ground installation shall be 316 stainless steel. All fittings shall be epoxy coated and lined unless stainless steel is used.

Where joints are to be restrained, use mega-lug type fitting for pipe six (6") inches in size and larger. Mega-lug type mechanical restraints with less than 6 contact points will not be allowed for six (6") inch pipe sizes and larger. Four (4") inch lines shall be restrained by mid-co restraint or pre-approved equal.

Polyethylene wrap or encasement of metal fittings shall conform to AWWA C105. Joint tape shall be self sticking PVC or 8-mil-thick polyethylene.

- e. Joints: PVC water pipe shall be furnished with an elastomeric gasket at each joint and an integral thickened bell as part of each joint. Pipe and fittings must be assembled with a non-toxic lubricant. Provisions must be made at each joint for expansion and contraction. Refer to ASTM F477, D3139 and D3212.

B. GRAVITY SANITARY SEWER

1. Pipe

Flexible pipe and fittings shall be unplasticized polyvinyl chloride gravity sewer pipe shall be green in color, made from clean, virgin, NSF approved Class 12454-B PVC conforming to ASTM D1784. All pipe shall be new and have the ASTM designation, SDR, pressure rating and size stamped on the outside of each joint. All markings shall follow requirements of ASTM D3034.

Polyvinyl chloride (PVC) gravity pipe and fittings in sizes six inch (6") through twelve inch (12") shall conform to ASTM D3034 and be UL listed and approved by the National Sanitation Foundation. Pipe and fittings shall be SDR-26. Eighteen inch (18") pipe and fittings shall be SDR-26 and conform to ASTM F-679, be UL listed and approved by the National Sanitation Foundation.

C. SEWER FORCE MAIN AND PRESSURE PIPE

1. Pipe

- a. Polyvinyl chloride (PVC) pressure pipe, four (4) inch through eight (8) inch, shall be white in color and shall conform to the current ASTM D2241, AWWA – C900, or AWWA C909 standard, be UL listed, be approved by the Texas State Board of Insurance and the National Sanitation Foundation. PVC pipe pressure class shall be equal to or greater than twice the maximum calculated pressure of the force main.
- b. Polyvinyl chloride (PVC) pressure pipe shall be SDR-21 Class 200 and conform to the ASTM D2241 standard, be UL listed and approved by the National Sanitation Foundation, and shall be white in color. The outside diameter shall be identical to steel pipe.
- c. PVC Pressure Pipe shall be designed and tested in accordance with ASTM D1598, D1599, and D2152.
- d. Fittings for PVC pressure pipe shall be ductile-iron, and shall conform to AWWA C153, unless otherwise specified. Fitting joints shall be mechanical joints. Bolts and nuts for mechanical joints, or flanged ends will be of a high strength corrosion resistant low-alloy steel and shall conform to AWWA C111. Flange bolts and nuts for above ground installation shall conform to Appendix A of AWWA C115. Flange bolts and nuts for below ground installation shall be 316 stainless steel. All fittings shall be epoxy coated and lined unless stainless steel is used. Polyethylene wrap or encasement of metal

fittings shall conform to AWWA C105. Joint tape shall be self sticking PVC or 10-mil-thick polyethylene.

Where joints are to be restrained, use mega-lug type fitting.

- e. Joints: PVC water pipe shall be furnished with an elastomeric gasket at each joint and an integral thickened bell as part of each joint. Pipe and fittings must be assembled with a non-toxic lubricant. Provisions must be made at each joint for expansion and contraction. Refer to ASTM F477, D3139 and D3212.

2.2 TESTING REQUIREMENTS

See: SECTION 33 01 30 - TESTING OF GRAVITY SEWER SYSTEMS

SECTION 33 13 10 - HYDROSTATIC TESTING (Used for Waterlines & Sanitary Sewer Force Mains)

SECTION 33 13 00 - DISINFECTION OF WATERLINES

PART 3 – EXECUTION

3.1 TRENCHING

- A. See Standard Details.

3.2 JOINT ASSEMBLY

- A. Push-on joints shall be assembled as follows:
 1. Thoroughly clean the groove and bell and insert the gasket, making sure that it faces the proper direction and that it is correctly seated.
 2. Dirt or foreign material shall be cleaned from the spigot end to a point one inch (1") beyond the reference mark. A joint lubricant shall be used and applicable recommendations of the manufacturer shall be followed.
 3. Be sure that the spigot end is beveled, as square or sharp edges may damage or dislodge the gasket and cause a leak. Push the spigot end into the bell of the pipe while keeping the joint straight. Brace the bell while the beveled end is pushed under the ring, so that previously completed joints in the line will not be closed up. Make deflection after the joint is assembled.
 4. Push the spigot end in until the reference mark on the spigot end is flush with the end of the bell. If excessive resistance to insertion of the beveled end is encountered or the reference mark does not reach the flush position, disassemble the joint, and check the position of the ring. If it is twisted or pushed out of its seat, clean the ring, bell and beveled end and repeat assembly. Be sure both lengths are in proper alignment. If the ring was not out of position, measure the distance between the reference mark and beveled end, and check it against correct values from the manufacturer. Relocate the reference mark if it is out of position.
 5. Small pipe can be pushed into the bell end with a long bar. Large pipe requires additional power, such as a jack, lever puller, or backhoe. A timber header should be used between the pipe and jack or backhoe bucket to avoid damage to the pipe.
 6. At times when pipe laying is not in progress, the open ends of pipe shall be closed by watertight plug or other means pre-approved by the Engineer. The plug shall remain

in place until the trench is pumped completely dry. Care must be taken to prevent pipe flotation should the trench fill with water.

B. Mechanical joints shall be assembled as follows:

1. Wipe clean the bell and spigot end. The spigot end, bell, and gasket should be washed with a soap solution to improve gasket seating.
2. Place the gland on the spigot end with the lip extension toward the spigot end, followed by the gasket with the narrow edge of the gasket toward the spigot end of the pipe.
3. Insert the pipe into the bell and press the gasket firmly and evenly into the gasket recess. Keep the joint straight during assembly. Make deflection after joint assembly but before tightening the bolts.
4. Push the gland toward the bell and center it around the pipe with the gland lip against the gasket.
5. Align bolt holes and insert bolts, with bolt heads behind the bell flange, and tighten opposite nuts to keep the gland square with the bell.
6. Tighten the nuts in accordance with manufacturer’s recommendations.

C. When it is necessary to deflect pipe from a straight line in either the vertical or horizontal plane, or where long radius curves are permitted, the amount of deflection shall not exceed that shown in Table 1. Pipes greater than twelve-inches (12”) in diameter shall not be deflected.

TABLE 1 Maximum Deflection Full Length Pipe Push-on Type Joint		
Pipe Diameter in.	Deflection Angle Deg.	Minimum Radius of Curve ft. *
6	2.5	230
8	1.9	300
12	1.3	450

* All curvature results from the bending of pipe lengths. There is no deflection at the joint.

D. Cutting and Beveling

1. A square cut is essential to insure proper assembly. Use either a tubing cutter or a miter box and carpenter's fine-toothed hand saw or hacksaw. (Do not use standard pipe cutters. The cutting wheel will crush or damage the pipe.)
2. Use a factory-finished beveled end as a guide to determine the angle and length of taper. The end may be beveled using a Pilot beveling tool which will cut the correct taper automatically or a thin steel, "cheese-grater" type of hand tool, Stanley "Sureform" No. 399.
3. With a pencil or crayon, locate the reference mark at the proper distance from the bevel end as indicated by the manufacturer.

3.3 POLYETHYLENE TUBE PROTECTION

- A. All cast iron and ductile iron fittings shall be provided with 8 mil polyethylene tube protection. Completely cover all fittings and connections with polyethylene film held securely in place with joint tape or strapping according to the provisions of AWWA C105.

3.4 EMBEDMENT

- A. Install embedment as shown on the Plans and in accordance with SECTION 31 23 33 - EXCAVATING, TRENCHING, AND BACKFILLING.

3.5 TAPPING WATER LINES

- A. Where a tap occurs within a deflected section of pipe, utilize a fitting (ie: 8” x 1” tapped tee) in lieu of tapping the pipe.
- B. The tapping sleeve specified will be the Smith-Blair 662 or the Ford FTSS_Stainless Steel Tapping Sleeve with Epoxy Coated Flange for pipe sizes 6"-24".

3.6 GRAVITY SANITARY SEWER DEFLECTION TEST

- A. The sewer line shall be tested for deflection in accordance with SECTION 33 01 30 - TESTING FOR SANITARY SEWAGE GRAVITY SYSTEM.

END OF SECTION